



PHOENIX FENCE

EDMONTON

12816-156 STREET T5V 1E9
PHONE: (780) 447-1919
FAX: (780) 447-2512
TOLL FREE: 1-800-661-9847
E-MAIL: phoenix@phoenixfence.ca

CALGARY


6204-2nd STREET S.E. T2H 1J4
PHONE: (403) 259-5155
FAX: (403) 259-2262
TOLL FREE: 1-888-220-2525
E-MAIL: calgary@phoenixfence.ca

WEBSITE: www.phoenixfence.ca


Snow and Safety Fence



DLW or DM



WB



FYT



SF

Model	DLW4100X	DM504X	DM1004X	WB4100X	FYT4100X	SF4850X	SF48100X
Description	Diamond Barrier Standard	Diamond Barrier Heavy	Diamond Barrier Heavy	Warning Barrier Standard	Economy Snow Fence	Snow Fence	Snow Fence
Style	Diamond	Diamond	Diamond	Oval Flat	Oval Flat	Oval Flat	Oval Flat
Process	Non-oriented	Non-oriented	Non-oriented	Oriented	Oriented	Oriented	Oriented
Material	Polyethylene	Polyethylene	Polyethylene	Polyethylene	Polyethylene	Polyethylene	Polyethylene
Color Code*	X	X, G, W	X	X	X	X, B	X, B
Roll Width (ft)	4	4	4	4	4	4	4
Roll Length (ft)	100	50	100	100	100	50	100
Roll Diameter (in)	12	12	19	10	9	7	10
Roll Weight (lbs)	22	15	30	13	20	14	28
Mesh Size (in)	2 x 2	1.75 x 1.75	1.75 x 1.75	3.5 x 1.25	2.25 x 1.5	2.5 x 2	2.5 x 2
Porosity	N/A	N/A	N/A	N/A	60%	50%	50%
Tensile Strength** (lb ft/ft w)	4732	5206	5206	2350	1510	2956	2956
Ultraviolet Resistance	Stabilized	Stabilized	Stabilized	Stabilized	Stabilized	Stabilized	Stabilized

*COLOR CODED LEGEND: X – orange, G – green, W – white and B – Black.

**TENSILE STRENGTH determined by Cambridge Material Testing Limited using ASTM D638-96 Modified methods. Machine direction and between the knuckles. Test speed of 2" per minute.